

Articolo / Article	Persempra 4.0
--------------------	----------------------

Composizione / Composition	100% PL
----------------------------	----------------

Peso Gr/mtl / Weight Grs/lmt	650
------------------------------	------------

Altezza cm / Width cms	138/140
------------------------	----------------








Test Martindale UNI EN ISO 12947 - 2 EN 14465, appendix A	Colour degradation after 3000 rubs: 165 000 Giri / Rubs	4/5
---	---	------------

Solidità Luce / Colour Fastness to light UNI EN ISO 105-B02 Blue Scale 1/8	7
--	----------

Solidità Sfregamento / Colour Fastness to rubbing UNI EN ISO 105-X12 Gray Scale 1/5	4/5 Secco / Dry 4/5 Umido / Wet
---	--

Test Pilling UNI EN ISO 12945-2	Degradation average photographic scale 1/5: a 2000 giri / at 2000 revs	4/5
------------------------------------	---	------------

Manutenzione / Maintenance

Note/Notes: Dimensional stability to dry washing (UNI EN ISO 3175)
warp : +/- % weft : +/- %

Dimensional stability to washing (UNI EN ISO 6330)
warp : +/- % weft : +/- %

* The results are tested in the laboratory and they must be considered as indicative.

<p>ITALVELLUTI Polska Sp. z o.o. 33-386 Podegrodzie, Brzezna 495, tel./fax: 18 446 07 84 e-mail: italvelluti@italvelluti.pl www.italvelluti.eu</p>	 the art of italian fabrics
--	--