

# PERSEMPRA™

MADE IN ITALY 

## SCHEDA TECNICA TECHNICAL CARD

Data / Date

30.01.2017

Articolo / Article / <i>Tkanina</i>	Persempra 2.0
Composizione / Composition / <i>Kompozycja</i>	100% PL
Peso Gr/mtl / Weight Grs/lmt / <i>Waga gr/mtb</i>	610
Altezza cm / Width cms / <i>Szerokość cm</i>	138/140

### Odporność na ścieranie

Test Martindale

UNI EN ISO 12947 - 2

EN 14465, appendix A

Colour degradation after 3000 rubs:

165 000

Giri / Rubs / *Cykli*

### Solidità Luce / Colour Fastness to light / *Odporność kolorów na światło*

UNI EN ISO 105-B02

Blue Scale 1/8

7

### Solidità Sfregamento / Colour Fastness to rubbing / *Odporność kolorów na pocieranie*

UNI EN ISO 105-X12

Gray Scale 1/5

5

Secco / Dry / *Sucho*

5

Umido / Wet / *Mokro*

### Odporność na Pilling

Test Pilling

UNI EN ISO 12945-2

Degradation average photographic scale 1/5:

5

a 2000 giri / at 2000 revs

### Manutenzione / Maintenance / *Sposób czyszczenia*



Note/Notes: Dimensional stability to dry washing (UNI EN ISO 3175)

*Stabilność wymiaru przy praniu chemicznym (UNI EN ISO 3175)*

warp / *wątek*: +/- % weft / *osnowa*: +/- %

Dimensional stability to washing (UNI EN ISO 6330)

*Stabilność wymiaru przy praniu wodnym (UNI EN ISO 6330)*

warp / *wątek*: +/- % weft / *osnowa*: +/- %

\* The results are tested in the laboratory and they must be considered as indicative.

ITALVELLUTI Polska Sp. z o.o.  
33-386 Podegrodzie, Brzezna 495  
tel. 18 446 07 84 fax. 18 414 54 51  
e-mail: [italvelluti@italvelluti.pl](mailto:italvelluti@italvelluti.pl)  
[www.italvelluti.eu](http://www.italvelluti.eu)

italvelluti