

# PERSEMPRA™

MADE IN ITALY 

Data / Date

04.07.2018

## SCHEDA TECNICA TECHNICAL CARD

Articolo / Article / <i>Tkanina</i>	Persempra 4.0
Composizione / Composition / <i>Kompozycja</i>	100% PL
Peso Gr/mtl / Weight Grs/lmt / <i>Waga gr/mtb</i>	650
Altezza cm / Width cms / <i>Szerokość cm</i>	138/140

### Odporność na ścieranie

Test Martindale Colour degradation after 3000 rubs: 4/5  
UNI EN ISO 12947 - 2 **165 000** Giri / Rubs / *Cykli*  
EN 14465, appendix A

### Solidità Luce / Colour Fastness to light / *Odporność kolorów na światło*

UNI EN ISO 105-B02 **7**  
Blue Scale 1/8




### Solidità Sfregamento / Colour Fastness to rubbing / *Odporność kolorów na pocieranie*

UNI EN ISO 105-X12 **4/5** Secco / Dry / *Sucho*  
Gray Scale 1/5 **4/5** Umido / Wet / *Mokro*

### Odporność na Pilling

Test Pilling Degradation average photographic scale 1/5: **4/5**  
UNI EN ISO 12945-2 a 2000 giri / at 2000 revs

### Manutenzione / Maintenance / *Sposób czyszczenia*



Note/Notes: Dimensional stability to dry washing (UNI EN ISO 3175)  
*Stabilność wymiaru przy praniu chemicznym (UNI EN ISO 3175)*  
warp / *wątek*: +/- % weft / *osnowa*: +/- %  
Dimensional stability to washing (UNI EN ISO 6330)  
*Stabilność wymiaru przy praniu wodnym (UNI EN ISO 6330)*  
warp / *wątek*: +/- % weft / *osnowa*: +/- %

\* The results are tested in the laboratory and they must be considered as indicative.

ITALVELLUTI Polska Sp. z o.o.  
33-386 Podegrodzie, Brzezna 495  
tel. 18 446 07 84 fax. 18 414 54 51  
e-mail: [italvelluti@italvelluti.pl](mailto:italvelluti@italvelluti.pl)  
[www.italvelluti.eu](http://www.italvelluti.eu)

